

# Easy-Spred®



Brick



Block



Stone

## *Mixing Instructions:*

- Start Mixer
- Add at least 1/2 to 2/3 of the total water to be used
- Add Easy-Spred®
- Allow Easy-Spred® to mix for 60 to 90 seconds
- Add remaining ingredients in the usual or specified manner
- Mix until the material has the desired consistency

Note: A mixing time of 6 minutes is recommended

## *Key Benefits:*

- Improves workability
- Improves board life
- High compression and bond strength
- Reduces early stage shrinkage
- Reduces efflorescence
- Great flow and pumpability
- Enhances color performance
- User friendly
- Saves money

## *Field Prepared Type M Mortar:*

- 2 x 94# bags of Portland cement
- 1 x 7# bag of Easy-Spred®
- 6 cubic feet of sand

## *Field Prepared Type S Mortar:*

- 2 x 94# bags of Portland cement
- 1 x 7# bag of Easy-Spred®
- 9 cubic feet of sand

## *Field Prepared Type N Mortar:*

- 1 x 94# bag of Portland cement
- 1 x 7# bag of Easy-Spred®
- 6 cubic feet of sand

## *Admixture Dosage Rate:*

- 2% by cement weight

[www.easy-spred.com](http://www.easy-spred.com)

Easy-Spred® benefits almost any cementitious environment and has performed in mortars and grouts since the 1950's. Easy-Spred® is used as an admixture to improve the field performance and hardened properties of cementitious materials and also as a code recognized lime replacement. Easy-Spred® is recognized for use in all seismic zones by the International Building Codes.

Peninsula Products, Inc.

3014 W. Palmira Ave. Suite 200

Tampa, FL 33629

Office: 813.832.4080 Fax: 813.832.4202

Email: [info@easy-spred.com](mailto:info@easy-spred.com)

"The Miracle in Mortar"®



Easy-Spred®



Brick



Block



Stone

For More Than Half a Century



Built with Easy-Spred®